



Enhancing effect of γ -cyclodextrin on wound dressing properties of sacran hydrogel film



Nasrul Wathoni^{a,b}, Keiichi Motoyama^a, Taishi Higashi^a, Maiko Okajima^c, Tatsuo Kaneko^c, Hidetoshi Arima^{a,d,*}

^a Graduate School of Pharmaceutical Sciences, Kumamoto University, 5-1 Oe-honmachi, Chuo-ku, Kumamoto 862-0973, Japan

^b Faculty of Pharmacy, Universitas Padjadjaran, Jatinangor 45363, Indonesia

^c Japan Advanced Institute of Science and Technology (JAIST), 1-1 Asahidai, Nomi-shi, Ishikawa 923-1292, Japan

^d Program for Leading Graduate Schools "Health Life Science: Interdisciplinary and Global Oriented (HIGO) Program", Kumamoto University, Japan

ARTICLE INFO

Article history:

Received 20 July 2016

Received in revised form

24 September 2016

Accepted 26 September 2016

Available online 6 October 2016

Keywords:

Sacran hydrogel film

Cyclodextrin

Wound dressing

ABSTRACT

A wound dressing is one of the essential approaches for preventing further harm to cutaneous wounds as well as promoting wound healing. Therefore, to achieve ideal wound healing, the development of advanced dressing materials is necessary. Recently, we revealed that a novel megamolecular polysaccharide, sacran, has potential properties as a biomaterial in a physically cross-linked hydrogel film (HGF) for wound dressing application. In this study, to enhance the wound-healing properties of sacran hydrogel film (Sac-HGF) further, we fabricated and characterized novel Sac-HGFs containing cyclodextrins (CyDs). The sacran/ α -CyD film (Sac/ α -CyD-HGF) and sacran/ γ -CyD HGF (Sac/ γ -CyD-HGF), but not sacran/ β -CyD HGF (Sac/ β -CyD-HGF), were well prepared without surface roughness. Powder X-ray diffraction (XRD) patterns of the Sac/ γ -CyD-HGFs showed a totally amorphous state compared to that shown by Sac/ α -CyD-HGFs. Furthermore, the addition of γ -CyD to Sac-HGFs significantly increased the swelling ratio, porosity, and moisture content of the HGFs, compared to those of the Sac-HGF without CyDs. The Sac/ γ -CyD-HGFs were not cytotoxic against NIH3T3 cells, a murine fibroblast cell line. Notably, the Sac/ γ -CyD-HGFs significantly improved wound healing in mice, compared to that achieved with the Sac-HGF without γ -CyD. These results suggest that γ -CyD has the potential to promote the wound healing ability of Sac-HGF.

© 2016 Published by Elsevier B.V.

1. Introduction

Cutaneous wound healing, a natural biological reaction to skin injury, is a complex and intricate process [1,2]. Currently, the healing process is considered to consist of four stages. The hemostasis stage starts immediately after wound infliction, via platelet aggregation and fibrin clot formation. Then, the inflammatory stage can be identified by the presence of neutrophils for wound debridement as well as macrophages that release cytokines at the wound site. In the proliferative stage, fibroblasts penetrate the wound and deposit a new extracellular matrix to begin the re-epithelialization process. Finally, the synthesis of collagens and myofibroblasts facilitates further tissue remodeling processes [3,4]. All the stages must occur in the correct sequence and timespan to ensure complete healing [5].

A wound dressing plays a pivotal role in maintaining and producing a moist environment around the wound, which promotes cutaneous wound healing [6,7]. The moist environment provided by wound dressing materials is closely associated with the migration of epidermal cells in the re-epithelialization process and the formation of scar tissue in the inflammatory stage, in addition to the avoidance of tissue dehydration [8–10]. Presently, various hydrogel films (HGFs) are used as wound-dressing materials [11,12]. In particular, natural polymer-based hydrogels have attracted considerable attention because of their excellent swelling ability in aqueous solutions, biodegradability at the wound site, and hydrophilicity, which is important in drug delivery systems [13,14]. For example, konjac glucomannan films showed good biocompatibility and efficiently accelerated wound repair [15]. Additionally, the alginate films ionically crosslinked with calcium chloride (CaCl_2) had an impressive surface appearance and mechanical properties [16]. However, organic solvents and crosslinkers used often are potentially hazardous to the body [17]. Therefore, the physical crosslinking method, which does not require the addition

* Corresponding author at: Graduate School of Pharmaceutical Sciences, Kumamoto University, 5-1 Oe-honmachi, Chuo-ku, Kumamoto 862-0973, Japan.

E-mail address: arimah@gpo.kumamoto-u.ac.jp (H. Arima).